

# WOLFRACOAT C FLUID

High-temperature lubricating compound



## Benefits for your application

- **Very good corrosion protection** → increased component lifetime
- **Ready-for-use** → just mix vigorously
- **Low consumption** → low costs, high efficiency
- **Easy application** → reduces maintenance time
- **Easier to mix in smaller canisters** → less effort required
- **No part-used stock** → the 5 l pack size matches the tank of the Klübermatic KD spray pump

## Description

WOLFRACOAT C FLUID is a viscous high-temperature release agent and lubricating compound based on a mineral and ester oil mixture. It contains solid lubricants, metal pigments and an inorganic thickener. The base fluid starts to evaporate at approx. 200°C, leaving a solid lubricant film, which separates frictional surfaces (dry lubrication).

## Application

WOLFRACOAT C FLUID was developed as a lubricating compound for surfaces subject to high thermal loads, as e.g. in rotary kilns in the base material industry (chemical industry, cement, ore processing, etc.) between the inner surfaces of the tyres and the kiln shell's slide elements as well as the running surfaces of the axial supports. WOLFRACOAT C FLUID is also suitable for the lubrication of pouring ladles used in the steel industry, and could also be used as a screw compound for high-temperature bolt and screw connections.

## Application notes

WOLFRACOAT C FLUID is usually applied to the area between the tyre and the kiln shell with the Klübermatic KD manual spray

jet equipment (other commercially available spray devices can also be used). In other cases the product can also be applied by brush. Each tyre should be relubricated once a week with 2-3 litres of WOLFRACOAT C FLUID according to the tyre width. It is important to ensure relative motion between the tyre and the kiln shell. We recommend reference to the relative motion value stated by the OEM (between 10 and 30 mm).

NOTE: Always shake WOLFRACOAT C FLUID vigorously prior to application, as the solid lubricants tend to settle out during storage. Without agitation, the spray jet would be filled only with the oil component, which would not provide dry lubrication following evaporation. Additionally, the oil component has an auto-ignition point of approx. 370 °C which may constitute a risk.

## Material safety data sheets

Material safety data sheets can be requested via our website [www.klueber.com](http://www.klueber.com). You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	WOLFRACOAT C FLUID
Canister 5 l	+
Canister 20 l	+



# WOLFRACOAT C FLUID

High-temperature lubricating compound

Product data	WOLFRACOAT C FLUID
Article number	099118
Lower service temperature	-25 °C / -13 °F
Upper service temperature	1050 °C / 1922 °F
Texture	homogeneous
Texture	very viscous
Colour space	grey
Density at 20 °C	approx. 1.03 g/cm <sup>3</sup>
Worked penetration, acc. to Klein, 25 °C, lower limit value	800 x 0.1 mm
Worked penetration, acc. to Klein, 25 °C, upper limit value	900 x 0.1 mm
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 150 mm <sup>2</sup> /s
Ignition temperature, DIN 51794	>= 370 °C
Solid lubricants, percentage	approx. 16 % by weight
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	24 months

## Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /  
Geisenhausenerstraße 7 / 81379 München / Germany /  
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.



a company of the Freudenberg Group