

STABURAGS N 12 MF

Long-term lubricating grease for plain and rolling bearings



Benefits for your application

- **Good corrosion protection**
- **Reduces wear**
- **Good emergency lubrication properties due to solid lubricant**

Description

STABURAGS N 12 MF is a mineral oil grease for long-term applications, as well as plain and rolling bearings operating at high temperatures and medium speeds. The solid lubricant it contains (MoS₂) ensures emergency operation at increased temperatures or loads.

Application

For the lubrication of bearings operating at high temperatures in fans, spline shafts, exhaustors and hot air blowers. Especially suitable for long-term lubrication of electric motors and enclosed rolling bearings which are not relubricated.

Application notes

STABURAGS N 12 MF is applied by brush, spatula or conventional metering systems.

Material safety data sheets

Material safety data sheets can be requested via our website www.klueber.com. You may also obtain them through your contact person at Klüber Lubrication.

Pack sizes	STABURAGS N 12 MF
Cartridge 400 g	+
Can 1 kg	+
Bucket 25 kg	+



STABURAGS N 12 MF

Long-term lubricating grease for plain and rolling bearings

Product data	STABURAGS N 12 MF
Article number	017016
Lower service temperature	-20 °C / -4 °F
Upper service temperature	140 °C / 284 °F
Speed factor (n x dm)	approx. 500 000 mm/min
Worked penetration, DIN ISO 2137, 25 °C, upper limit value	275 x 0.1 mm
Worked penetration, DIN ISO 2137, 25 °C, lower limit value	245 x 0.1 mm
Kinematic viscosity, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 100 °C	approx. 19 mm ² /s
Kinematic viscosity of the base oil, DIN 51562 pt. 01/ASTM D-445/ASTM D 7042, 40 °C	approx. 220 mm ² /s
Shear viscosity at 25°C, shear rate 300 s ⁻¹ , equipment:rotational viscometer, upper limit value	9 000 mPas
Shear viscosity at 25 °C, shear rate 300 s ⁻¹ , equipment: rotational viscometer, lower limit value	6 000 mPas
Drop point, DIN ISO 2176	>= 220 °C
Colour space	black
Chemical composition	molybdenum disulphide
Chemical composition, thickener	sodium complex soap
Chemical composition, type of oil	mineral oil
Density at 20 °C	approx. 0.95 g/cm ³
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

Klüber Lubrication – your global specialist

Innovative tribological solutions are our passion. Through personal contact and consultation, we help our customers to be successful worldwide, in all industries and markets. With our ambitious technical concepts and experienced, competent staff we have been fulfilling increasingly demanding requirements by manufacturing efficient high-performance lubricants for more than 80 years.

**Klüber Lubrication München SE & Co. KG /
Geisenhausenerstraße 7 / 81379 München / Germany /
phone +49 89 7876-0 / fax +49 89 7876-333.**

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication München SE & Co. KG. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication München SE & Co. KG and if source is indicated and voucher copy is forwarded.



a company of the Freudenberg Group