

Product Data

Castrol Braycote 248

Corrosion Preventive Compound Petrolatum, Hot or Cold Application, Soft Film

Description

Braycote 248 is designed to protect machined, unpainted metal surfaces from the effects of indoor or shed exposure for periods of six months or more. It is especially suitable for the preservation of anti-friction bearings in storage or shipment.

Application

Braycote 248 may be applied by dipping at temperatures from 160°F to 180°F (71°C to 82°C). It may be brushed or swabbed on at room temperature when its consistency resembles a soft grease, or at elevated temperatures when it resembles an oil. Hot spray applications can be used for protecting large pieces of equipment that are too large in size for dipping applications. Optimal performance can be achieved only when the metal surfaces to be protected are clean, dry and free of rust, oil and mill scale.

The coverage of Braycote 248 will widely vary dependent on the method of application and surface geometries. Parts allowed to reach the temperature of the compound before removal from the tank. Approximate coverage and film thickness data for the different methods are given in the following table:

Method	Film Thickness Mils	Coverage Ft ² /Gal	
Quick Dip	30 to 60	30 to 50	
Brush or Swab, Hot 160°F to 180°F (71°C to 82°C)	5 to 20	80 to 300	
Brush or Swab	10 to 30	50 to 160	
Hot Spray, per coat	3 to 10	160 to 500	
Slow Dip 160°F to 180°F (71°C to 82°C) *	1.2 to 1.6	1000 to 1300	

Typical Characteristics

Test	Method	Units	MIL-C-11796C CLASS 3 REQUIREMENTS	Result
Penetration	ASTM D937		200-250	217
Melting Point	ASTM D127	°C/°F	57/135 Minimum	71/160
Flash Point	ASTM D92	°C/°F	177/350 Minimum	262/505
Sulfated Residue	ASTM D874	%	0.15 +/-0.05	0.19
Stability	Spec 4.6.2	Pass/Fail	No Separation or Foam	Pass
Volatility	Spec 4.6.3	%	1.0 Maximum	0.36
Miscibility with Grade 100 Mil-L-6082 Oil	Spec 4.6.5	Pass/Fail	No separation	Pass
Abrasives	Spec 4.6.6	ml (Pass/Fail)	0.05 Maximum	Pass
Applicability, thickness of coating	Spec 4.6.8.1	mils (Pass/Fail)	1.50 +/-0.2	Pass
Humidity Cabinet, 30 days minimum	Spec 4.6.8.1	Pass/Fail	Pass	Pass
Corrosiveness Aluminum Brass Cadmium Steel Magnesium Zinc Lead Stain Test Original Material 5% Emulsion	Spec 4.6.8.3 Spec 4.6.8.4	mg/cm² Pass/Fail	++-0.2 Maximum ++-0.2 Maximum ++-0.2 Maximum ++-0.2 Maximum ++-0.5 Maximum ++-0.2 Maximum ++-1.0 Maximum Pass Pass Pass	0.019 0.039 0.0042 0.049 0.008 0.0038 0.063 Pass Pass
Low Temperature Adhesion, -40°C/-40°F	Spec 4.6.9	Pass/Fail	Pass	Pass
Flow Point, 50-55 mils	Spec 4.6.10	°C / °F	54/130 Minimum	Pass

Subject to usual manufacturing tolerances.

Additional Information

Removal

Braycote 248 may be removed by solvent or steam cleaning.

Packaging

Braycote 248 is available in 400 pound drums, 35 pound pails and 12/1 pound cases.

Specifications

Braycote 248 meets the requirements of specification and is qualified to MIL-C-11796C, Class 3. This product is identified by NATO Code: C-627.

Castrol, Braycote, and the Castrol logo are trademarks of Castrol Limited, used under licence

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet.

It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol Limited, Pipers Way, Swindon, Wiltshire SN3 1RE, UK www.castrol.com/industrial www.castrol.com/industrial