

PRODUCT DATA

RUST VETO 344

A black, liquid rust preventive, which contains a volatile solvent. Shortly after application the solvent will evaporate to leave a black film which, while it is dry to the touch, will remain soft enough to expand or contract with the coated surfaces without cracking, chipping or flaking off.

INTENDED USES:

RUST VETO 344 is intended for the long term preservation of ferrous or non-ferrous metal parts which are to be stored indoors or outdoors, without wrapping, under the most severe climatic conditions.

METHODS OF APPLICATION:

RUST VETO 344 can be applied neat by brushing, dipping or spraying at room temperature. The product may be diluted with Stoddards Solvent for ease of spraying. When the product is applied as a dilution it is advisable to apply 2 coats and to allow the first to dry for 12 hours before the second is applied.

TYPICAL PHYSICAL PROPERTIES:

Appearance of product	Black Liquid
API Gravity @ 16°C	28.9
Flash Point (Minimum) (C.O.C.)	40°C
Pour Point	-6°C
Specific Gravity	1.056
Coverage	100 ft ² /Litre
Drying time (dust free)	4 hours
Film thickness (approximate by dipping)	0.08 mm



HOUGHTON CANADA INC.
P.O. Box 113, Station "D"
100 Symes Rd.
Toronto, Ontario M6P 3J5
Ph (416) 763-4691 • Fx (416) 763-3167

PROTECTION:

Humidity/Ultra violet light	
19 hours 100% humidity	30 Days
5 hours Ultra violet light	
Salt Spray (20% @ 38°C)	10 Days

ADVANTAGES:

RUST VETO 344 is a homogeneous liquid, It contains a volatile solvent, is easy to apply by brushing, dipping or spraying at room temperature, dries to form a flexible film which will not crack or flake off at temperatures down to -28°C. provides protection for long periods of time under the most severe climatic conditions,

RUST VETO 344 is especially recommended to protect parts which are too large to place in boxes or crates.

REMOVABILITY:

The film of **RUST VETO 344** can be removed by immersing the coated parts in a solvent degreaser or in a petroleum solvent such as Stoddard Solvent or kerosene.

When using a petroleum solvent, the coated parts should be immersed in or wetted by the solvent and, when the film has been softened it should be wiped off with rags saturated with the solvent.

AVAILABILITY:

RUST VETO 344 is made in Canada and is sold in 20 litre pails and 205 litre drums.

STORAGE/HANDLING/DISPOSABILITY

No health or safety hazards exist when **RUST VETO 344** is stored, used and disposed of in accordance with instructions given on the Material Safety Data Sheet for this product.

WARRANTY

The information given here is considered to be correct and is offered for your consideration, investigation and verification. No warranties are expressed or implied since the use of our products is beyond our control. Statements concerning the use of Houghton products are not to be construed as recommending the infringement of any patent.

April 27, 2005