

# RUST VETO SKR

## Data Sheet

### RUST PREVENTIVE FOR SHEETS, BARS AND SECTIONS

RUST VETO SKR is a rust preventive fluid which leaves a fatty, thin lubricant film on the pieces. RUST VETO SKR has been especially studied by Houghton Laboratories for the prevention of cold rolled sheets, tubes, bars and sections during the carriage and the storage under difficult environmental conditions.

#### TYPICAL PHYSICAL AND PROTECTIVE PROPERTIES

Appearance	Clear liquid
Colour	Amber
Flammability COC	174°C
Specific Weight at 15.5°C	0.897
Viscosity at 40°C CsT	29 ± 2
Protection time	One year indoor Six months outdoor
Film thickness	15 µ
Removal of film	Cold solvents
Humidity Cabinet Test Resistance	> 20 cycles

#### ADVANTAGES :

- ❑ Easy to apply.
- ❑ High wettability.
- ❑ Good resistance to atmospheric agents.
- ❑ Easy to remove by cleaners or degreasing agents (cold).
- ❑ Excellent lubricant qualities.
- ❑ Total compatibility with lubricant oils and greases and with drawing and deep-drawing products.
- ❑ Particular formulation and special raw materials contained avoid the drying and the polymerisation of the protective film even after a long storage time of the protected piece.

The information contained in this product data sheet must not be considered as a specification, warranty, or as possible suggestions to infringe any patent.

## APPLICATION

RUST VETO SKR can be applied through specific drips, by immersion, by brush, through electrostatic devices or sprayed.

RUST VETO SKR is supplied in drums (180 kilos) or bulk (packages 1.000 kilos about )

## HEALTH & SAFETY

No toxic or carcinogenic, teratogenic or mutagenic known materials are contained in RUST VETO SKR such as nitrosamines, phenols, polychlorinated diphenyl, heavy metals, polinuclear hydrocarbons.

## STORAGE

RUST VETO SKR maintains its chemical-physical and technical characteristics if stored in a sheltered place at a temperature of  $-5^{\circ}\text{C}$  and  $+40^{\circ}\text{C}$  maximum for a period of twelve months.

## WASTE TREATMENT

RUST VETO SKR cannot be directly discharged. Follow national or local instructions.

M/03- X0340-APPROVAL : D.PETTA